



7 hari Beton Normal
240 KN

7 hari Beton Normal
220 KN

7 hari Beton Normal
210 KN



14 hari Beton Normal
310 KN

14 hari Beton Normal
300 KN

14 hari Beton Normal
312 KN



28 hari Beton Normal
400 KN

28 hari Beton Normal
400 KN

28 hari Beton Normal
395 KN



7 hari 10% 170 KN

7 hari 10% 195 KN

7 hari 10% 160 KN



7 hari 20% 160 KN

7 hari 20% 225 KN

7 hari 20% 100 KN



7 hari 30% 245 KN

7 hari 30% 165 KN

7 hari 30% 280 KN



14 hari 10% 160 KN 14 hari 10% 280 KN 14 hari 10% 190 KN



14 hari 20% 205 KN 14 hari 20% 330 KN 14 hari 20% 210 KN



14 hari 30% 220 KN 14 hari 30% 290 KN 14 hari 30% 235 KN



28 hari 10% 260 KN

28 hari 10% 220 KN

28 hari 10% 280 KN



28 hari 20% 160 KN

28 hari 20% 390 KN

28 hari 20% 270 KN



28 hari 30% 335 KN

28 hari 30% 310 KN

28 hari 30% 345 KN



Agregat Kasar Tertahan Pada Tapis 4/3"



Agregat Kasar Tertahan Pada Tapis 1/2"



Agregat Kasar Tertahan Pada Tapis 3/8"



Agregat Halus Tertahan Pada Tapis 2 mm



Kerucut Abrams



Molen (mesin Pengaduk)



Mesin Pengayak



Compression Test Machine