

7 8 b69f187e-d775-487e-8a0b-
2136a19e1d87-71-81.pdf

by Yosafat Pranata

Submission date: 15-Jan-2025 08:22AM (UTC+0700)

Submission ID: 2564350680

File name: 7_8_b69f187e-d775-487e-8a0b-2136a19e1d87-71-81.pdf (608.22K)

Word count: 3634

Character count: 18007

Flexural Behavior of Indonesian Berua Timber: Experimental Test and Numerical Analysis



Yosafat Aji Pranata, Anang Kristianto, and Novi

Abstract The bending behavior of timber beams in a frame systems of modular timber house or permanent timber house needs to be known, specifically for the mechanical properties of bending forces, modulus of rupture, and modulus of elasticity. These three parameters are important parameters for the purposes of timber beam design in timber buildings both for non-multistorey and multistorey. One of the experimental testing methods in the laboratory for flexural or bending tests is based on the ASTM D143-21 Standard. The purpose of this study is to do the nonlinear finite element modeling of timber beam and experimental testing in the laboratory that is a flexural test to determine the behavior of beams. The scopes of the research, namely the bending behaviors, reviewed are as follows: the parameters of bending strength, modulus of rupture, and modulus of elasticity, the timber studied is Indonesian Berua timber, and bending testing is based on the ASTM standard reference which is D143-21. The method that used in this study is based on experimental tests numerical analyses to obtain the empirical parameter of the bending strength. The results showed that the average flexural strength of timber with experimental test results obtained by 31.52 MPa, modulus of rupture 46.68 MPa, and modulus of elasticity 4143.51 MPa, while the results of the nonlinear finite element modeling showed the bending strength of 29.33 MPa (% difference with experimental results is - 6.96%), modulus of rupture 49.63 MPa (% difference with experimental results is 6.34%), and modulus of elasticity 3477.19 MPa (% difference with experimental results is - 16.09%). These results show that in general the nonlinear finite element modeling produces values that are close to the results of experimental testing. One of the important benefits of numerical modeling is to study the behavior of buildings due to working loads so that predictions of strength, rigidity, and stability behavior can be known. This is important as a reference to the feasibility requirements of the design of a building.

Keywords Flexural strength · Modulus of elasticity · Berua timber · Nonlinear finite element modeling

2 A. Pranata (✉) · A. Kristianto · Novi
Faculty of Engineering, Universitas Kristen Maranatha, Kota Bandung, West Java 40164,
Indonesia
e-mail: yosafat.ap@gmail.com

© The Author(s), under exclusive license to Springer Nature Singapore Pte Ltd. 2025
E. Strauss (ed.), *Proceedings of the 8th International Conference on Civil Engineering*,
Lecture Notes in Civil Engineering 539, https://doi.org/10.1007/978-981-97-5910-1_5

1 Introduction

Timber beams are one of the main components of frame structure, with the function to withstand the internal forces that work on the builds which are shear forces and flexural moments. The three main parameters in the design of a bending structure component are the bending strength (F_b), the modulus of elasticity (MoE), and the modulus of rupture (MoR). Bending strength is used as a parameter in the calculation of corrected bending capacity, modulus of elasticity is used as a parameter in the calculation of beam deflection, while modulus of rupture is also used as a parameter in the calculation of bending capacity. One empirical method of testing bending wood is to use the ASTM D143-21 [1] reference.

Research history or publication of timber bending strength research has been done previously, namely Pranata and Suryoatmono [2], which is the nonlinear finite element analysis/modeling for compression of one Indonesian timber species. In this research, the compressive strength and modulus of elasticity of the red Meranti timber was studied numerically based on nonlinear finite element modeling and empirically through experimental testing in the laboratory. Subsequent research on the bending strength, MoE, and MoR for Ulin timber (*Eusideroxylon zwageri*) has also been conducted by Pranata and Palapessy [3] with results that are the flexural strength, MoE, and MoR Ulin timber parameters. Research related to modulus of elasticity has also been conducted on existing buildings, which is a traditional Minangkabau house located in North Sumatra Indonesia by Pranata and Tobing [4] and nondestructive testing to obtain the dynamic elastic modulus of the existing Minangkabau wooden house; the results obtained from this research are as follows: The column modulus of elasticity (average) is 12670.08 MPa, the floor beam modulus of elasticity (average) is 13119.00 MPa, the roof beam modulus of elasticity (average) is 12997.37 MPa, the floor board modulus of elasticity (average) is 11151.11 MPa, and the timber wall modulus of elasticity (average) is 12976.00 MPa. Numerical modeling of timber and timber joints research including the failure mode could be identified using this FEA approach [5]. Semi-destructive of timber mechanical properties also can be done using both experimental and numerical analyses [6]. Numerical simulation can be used for studying about the acoustic wave propagation in standing trees [7]. Orthotropic material, especially the three-dimensional nonlinear simulation for timber research, also studied before [8].

The purposes of this research are to do the nonlinear finite element modeling of timber beam and experimental testing in the laboratory that is a flexural test to find out the behavior of timber bending. The scopes of the research of the flexural behavior reviewed are the parameters of bending strength, modulus of rupture, and modulus of elasticity. The timber that studied is Berua timber originating from the Nias Island in Indonesia, and bending testing is based on the reference regulation's ASTM D143-21 [1]. Numerical analysis based on the nonlinear finite element modeling is done using ADINA software [9], and the cross-section size of the test object is 140 × 140 mm with 760 clear span length.




Fig. 1 Classification of beam bending failures in accordance with ASTM [1]

2 Basic Theory

2.1 Timber Flexural Behavior

The bending strength is the limit strength that timber can achieve when the timber component fails due to bending [10]. Based on ASTM D143-21 [1], the criterion for static bending flexural failures with the center-point loading test object model consists of several classifications depending on the condition of the surface crack. Classifications of beam failure are simple tension, cross-grain tension, splinter tension, brash tension, compression, and horizontal shear. Schematic beam failure due to full a bending load is shown in Fig. 1. The type of simple tension failure (Fig. 1a) is a crack in the outermost fiber of the pull and then cracks spread in the parallel direction of the fiber.

The type of cross-grain tension failure (Fig. 1b) is a crack in the outermost fiber of the pull section with the direction of crossing cracking or crossing the direction of the fiber. Splinter tension failure type (Fig. 1c) is in the outermost fiber of the pull; there is a shale-shaped crack so that the wood splits. The type of brash tension failure (Fig. 1d) is a crack that is brittle or brittle in the outermost fiber of the pull. The compression failure type (Fig. 1e) is a crack occurring in the outermost fiber of the compressed part. The horizontal shear failure type (Fig. 1f) is a creeping crack following the direction of the fiber or called shear failure.

2.2 Orthotropic Material

Within the range of a particular promotional boundary, material behavior is modeled as orthotropic elastic linear behavior. The constitutive behavior of orthotropic elastic linear material can be described under Hooke's law [11, 12].

$$\begin{Bmatrix} \varepsilon_L \\ \varepsilon_R \\ \varepsilon_T \\ \gamma_{RT} \\ \gamma_{LT} \\ \gamma_{LR} \end{Bmatrix} = \begin{bmatrix} \frac{1}{E_L} & -\nu_{RL} & -\nu_{TL} & 0 & 0 & 0 \\ \frac{-\nu_{LR}}{E_L} & \frac{1}{E_R} & -\nu_{TR} & 0 & 0 & 0 \\ \frac{-\nu_{LT}}{E_L} & -\nu_{RT} & \frac{1}{E_T} & 0 & 0 & 0 \\ 0 & 0 & 0 & \frac{1}{G_{RT}} & 0 & 0 \\ 0 & 0 & 0 & 0 & \frac{1}{G_{LT}} & 0 \\ 0 & 0 & 0 & 0 & 0 & \frac{1}{G_{LR}} \end{bmatrix} \begin{Bmatrix} \sigma_L \\ \sigma_R \\ \sigma_T \\ \tau_{RT} \\ \tau_{LT} \\ \tau_{LR} \end{Bmatrix} \quad (1)$$

Shear modulus [13] for all tree directions in this research are calculated using equations,

$$G_{LR} = \frac{E_L \cdot E_R}{E_L \cdot (1 + \nu_{LR}) + E_R \cdot (1 + \nu_{RL})} \quad (2)$$

$$G_{LT} = \frac{E_L \cdot E_T}{E_L \cdot (1 + \nu_{LT}) + E_T \cdot (1 + \nu_{TL})} \quad (3)$$

$$G_{RT} = \frac{E_R \cdot E_T}{E_R \cdot (1 + \nu_{RT}) + E_T \cdot (1 + \nu_{TR})} \quad (4)$$

The orthotropic plastic material model based on Hill's yield criteria [12] is an extension of von Mises' yield criteria:

$$f(\sigma_{ij}) = F(\sigma_{bb} - \sigma_{cc})^2 + G(\sigma_{cc} - \sigma_{aa})^2 + H(\sigma_{aa} - \sigma_{bb})^2 + 2L\sigma_{ab}^2 + 2M\sigma_{ac}^2 + 2N\sigma_{bc}^2 - 1 = 0 \quad (5)$$

$$F = \frac{1}{2} \left(\frac{1}{Y^2} + \frac{1}{Z^2} - \frac{1}{X^2} \right) \quad (6)$$

$$G = \frac{1}{2} \left(\frac{1}{Z^2} + \frac{1}{X^2} - \frac{1}{Y^2} \right) \quad (7)$$

$$H = \frac{1}{2} \left(\frac{1}{X^2} + \frac{1}{Y^2} - \frac{1}{Z^2} \right) \quad (8)$$

$$L = \frac{1}{2Y_{ab}^2} \quad (9)$$

$$M = \frac{1}{2Y_{ac}^2} \quad (10)$$

$$N = \frac{1}{2Y_{bc}^2} \quad (11)$$

Here, a, b, c are the three principal directions, while X, Y, Z are yield stresses at the direction a, b, c and Y_{ab}, Y_{ac}, Y_{bc} are yield stresses for pure shear for all the three planes $(a, b), (a, c),$ and (b, c) .

2.3 Determining Yield Point

Proportional limit load determination using the Yasumura and Kawai [14] method is a method that has been applied to research with timber structure element test objects and timber frame structures. In the Yasumura and Kawai methods, initial stiffness (in the form of a straight line) is calculated between the range of a 10 and 40% maximum load. It further defined a straight line between two points where the values are 40 and 90% the maximum load. The yield point is determined from the meeting of the two lines (see Fig. 2). P_y can be used to obtain F_b , which is $M_{y,y}/I_x$ (mechanics of material equation) while P_u can be used to obtain MoR, which is also $M_{u,y}/I_x$.


$$F_y = M_{y,y}/I_x \quad \text{where} \quad M_y = P_y \cdot L/4 \quad (12)$$

$$\text{MoR} = M_u \cdot y/I_x \quad \text{where} \quad M_u = P_u/L/4 \quad (13)$$

$$D_y = P \cdot L^3 / (48 \cdot \text{MoE} \cdot I_x) \quad (14)$$

$$\text{MoE} = P \cdot L^3 / (48 \cdot D_y \cdot I_x) \quad (15)$$

Fig. 2 Determining yield point in accordance with Yasumura and Kawai method [14]



2.4 Finite Element Analysis

A 3-D solid element is a three-dimensional solid model that is not limited to shape, loading, material properties, and boundary conditions [9, 15]. Consequently, there are likely to be six voltage values (three normal stresses and three shear stresses) and the transition that occurs in three directions, namely u , v , and w . Material stress and strain measurement method [9] for small strain models is defined for strains with a value of less than 2%. The assumption of the small displacement/small strain model uses the assumption that input data are a curve model of engineering stress and engineering strain relationship, and then, output data are a model of Cauchy stress relationship curve and engineering strain while the large displacement/large strain model uses the assumption of output data which is a model of the relationship curve Kirchhoff stress and left Hencky strains or Jaumann strains.

Nonlinear finite element analysis to predict the flexural behavior of timber beam can be done using a FEA software named ADINA [9]. The stress-strain curves for all three principal axes of the orthotropic material are modeled using the Hill's yield equations. The relationship between the yield stress and the plastic strain can be used determining the hardening rule in terms of t . The 3-D element of solid is a 20-node isoparametric element applicable to 3-D analysis. A numerical model of the specimen is modeled using the 3-D quadric element with 20 nodes as shown in Fig. 3.

The equilibrium equations [9] to be solved are as follows:

$${}^{t+\Delta t}R - {}^{t+\Delta t}F = 0 \quad (16)$$

Here, ${}^{t+\Delta t}R$ is the vector of applied nodal loads, and ${}^{t+\Delta t}F$ is the equivalent force vector to the element stresses. The arc length method or the load-displacement control (LDC) method can be used to solve the nonlinear equilibrium of a model until collapse. The arc length method can be used in a nonlinear static analysis for incremental loads. The arc length method can also be used in contact problems [9]. The equations are as follows:

$${}^{t+\Delta t}K^{(i-1)}\Delta U^{(i)} = ({}^{t+\Delta t}\lambda^{(i-1)} + \Delta\lambda^{(i)})R + R_p - {}^{t+\Delta t}F^{(i-1)} \quad (17)$$

$${}^{t+\Delta t}U^{(i)} = {}^{t+\Delta t}U^{(i-1)} + \Delta U^{(i)} \quad (18)$$

$$f(\Delta\lambda^{(i)}, \Delta U^{(i)}) = 0 \quad (19)$$

Fig. 3 Quadric element with 20 nodes [9]



12

Here, the tangent stiffness matrix ${}^{t+\Delta t}K^{(i-1)}$ is used at the end of iteration $(i - 1)$ at time $t + \Delta t$, R is vector in terms of constant load, R_p is the load vector that obtained from previous run, and the load scaling factor ${}^{t+\Delta t}\lambda^{(i-1)}$ is used at the iteration of $i - 1$ at time $t + \Delta t \cdot \Delta\lambda^{(i)}$ is the increment in the load scaling factor.

18


3 Experimental Test, Results, and Discussion

3.1 Experimental Test

The results of an experimental study of Berua timber beam test objects are shown in Fig. 4. Testing is done using the universal testing machine. The testing method is the third point bending test in accordance with ASTM D143-21 [1] or also called the center-point loading test method. The speed of a crosshead is 2.5 mm/min. The model of bending test objects used in this study uses references based on the specifications of primary test objects (primary method with a net span length of 760 mm beams). The test object is made with a cross-sectional size of 140×140 mm with a total length of wood beams is 920 mm. Furthermore, the beam mounted on the bending test mount with a clear distance is 760 mm according to ASTM 143–21 [1].

Figure 4 shows the testing process of the B-N-01 test object which is the stage of the test object setup and continued with the bending testing process. Figure 5 shows the results of the destructive test that is the beam bending test. In general, the beam failure pattern is simple tension failure for all test objects which are B-N-01, B-N-02, and B-N-03.


Furthermore, Fig. 6 shows beam modeling using the nonlinear finite element method. Beam element modeling uses a solid 3-D element type, while mesh modeling uses quadric element type with 20 nodes. The test results are that the relationship curve between a load and beam deformation is more displayed in Fig. 7 and Table 1. Calculation of the load at proportional limit conditions (yield points) and the ultimate load is done on the basis of the theory of the Yasumura and Kawai methods [10].



3

Fig. 4 Setup of the beam specimen in universal testing machine

Fig. 5 Failure of the beam specimens due to destructive tests



19

The result of numerical analysis is displayed in Fig. 7, and the results of calculation of the proportional limit load and the ultimate loads are displayed in Table 1.

Fig. 6 Schematic 3D finite element modeling of Berua timber beam





Fig. 7 Results obtained from both experimental and numerical analyses: the load versus beam deformation

Table 1 Bearing load (peak) ³ obtained from experimental tests

Specimen	P_y (N)		D_y (mm)	P_u (N)	D_u (mm)	
B-N-01	78,573.00	75,874.33	6.14	119,330.00	112,350.67	12.63
B-N-02	65,167.00		5.70	93,784.00		12.26
B-N-03	83,883.00		4.35	123,938.00		6.34
FEA	70,597.22	70,597.22	5.80	119,472.00	119,472.00	13.90

The % difference of P_y between experimental test results (average value) and FEA is -6.96% which is indicated that P_y obtained from FEA (70,597.22) is lower than experimental test results (75,874.33 N). The % difference of P_u between experimental test results (average value) and FEA is 6.34% which is indicated that P_u obtained from FEA (119,472.00) is higher than experimental test results (112,350.67 N). These P_y (proportional load) results indicate that modeling with FEA results in lower values than experimental results. The advantage of numerical analysis with FEA in this study is the existence of accurate proportional limit load predictions. This is important for the purposes of predicting the capacity of structural components. With an accurate prediction of the capacity of the components, it can be predicted and also known the capacity of buildings that can be held due to the burdens of both gravity and lateral loads (earthquakes) that hit the building.

Bending or flexural strength (F_b), MoE (modulus of elasticity), and MoR (modulus of rupture) parameters can be calculated using Eqs. 12–15. The results are shown in Tables 2 and 3. These results indicated that the MoE obtained from FEA (3477.19 MPa) is -16.08% lower than the MoE obtained from experimental tests (4143.51 MPa), the F_b obtained from FEA (29.33 MPa) is -6.96% lower than the F_b obtained from experimental tests (31.52 MPa), while the MoR obtained from FEA (49.63 MPa) is 6.34% higher than the MoR obtained from experimental tests (46.68 MPa). The MoR parameter obtained from FEA is higher than the experimental tests because B-N-02 has the lowest value both for P_y and P_u .

Table 2 Numerical and experimental results: MoE (MPa)

Specimen	F_b (MPa)		MoR (MPa)	
B-N-01	32.64	31.52	49.58	46.68
B-N-02	27.07		38.96	
B-N-03	34.85		51.49	
FEA	29.33	29.33	49.63	49.63

Table 3 Numerical and experimental results: MoR (MPa)

Specimen	P_y (N)	D_y (mm)	MoE (MPa)	
B-N-01	78,573.00	6.14	3655.73	4143.51
B-N-02	65,167.00	5.70	3266.04	
B-N-03	83,883.00	4.35	5508.75	
FEA	70,597.22	5.80	3477.19	3477.19

4 Conclusion

The results showed the average flexural strength of timber with experimental test results obtained by 31.52 MPa, modulus of rupture 46.68 MPa, and modulus of elasticity 4143.51 MPa, while the results of the nonlinear finite element modeling showed the bending strength of 29.33 MPa (% difference with experimental results is – 6.96%), modulus of rupture 49.63 MPa (% difference with experimental results is 6.34%), and modulus of elasticity 3477.19 MPa (% difference with experimental results is – 16.09%). These results show that in general the nonlinear finite element modeling produces values that are close to the results of experimental testing. One of the important benefits of numerical modeling is to study the behavior of buildings due to working loads so that predictions of strength, rigidity, and stability behavior can be known. This is important as a reference to the feasibility requirements of the design of a building.

Acknowledgements The authors would like to acknowledge Universitas Kristen Maranatha for financial support for the research (a fund substitution scheme or “Skema Substitusi Dana,” fiscal year 2021) and the Structural Laboratory for conducting timber shear testing.

References

1. American Society for Testing and Materials: ASTM D143-21 Standard Test Methods for Small Clear Specimens of Timber, American Society for Testing and Materials, 100 Barr
2. Pranata, Y.A., Suryoatmono, B.: Nonlinear finite element modeling of red Meranti compression at an angle to the grain. *J. Eng. Technol. Sci.* **45**(3), 222–240 (2013)
3. Pranata, Y.A., Palapessy, J.G.: Flexural strength, MoE, and MoR of Ulin Timber (*Eu-sideroxylon Zwageri*). *J. Teknik Sipil* **13**(1) (2014). <https://doi.org/10.24002/jts.v13i1.641> (in Indonesian)
4. Pranata, Y.A., Tobing, H.L.: Non-destructive testing to obtain the dynamic elastic modulus of the existing Minangkabau wooden house, conference: international conference on technology. *Innov. Soc.* (2016). <https://doi.org/10.21063/ICTIS.2016.1060>
5. Sandhaas, C., Sarnaghi, A.K., van de Kuilen, J.W.: Numerical modelling of timber and timber joints: computational aspects. *Wood Sci. Technol.* **54**, 31–61 (2020). <https://doi.org/10.1007/s00226-019-01142-8>
6. Kloiber, M., Kunecký, J., Drdácý, M., et al.: Experimental and numerical analysis of semi-destructive device for in situ assessment of wood properties in compression parallel to grain. *Wood Sci. Technol.* **51**(345–356), 2017 (2017). <https://doi.org/10.1007/s00226-016-0881-6>

7. Liu, F., Wang, X., Zhang, H., Jiang, F., Yu, W., Liang, S., Fu, F., Ross, R.J.: Acoustic wave propagation in standing tress—part 1. *Numer. Simul. J. Wood Fiber Sci.* **52**(1) (2020)
8. Florisson, S., Vessby, J., Mmari, W., et al.: Three-dimensional orthotropic nonlinear transient moisture simulation for wood: analysis on the effect of scanning curves and nonlinearity. *Wood Sci. Technol.* **54**(1197–1222), 2020 (2020). <https://doi.org/10.1007/s00226-020-01210-4>
9. ADINA R&D, Inc.: ADINA AUI Theory and Modeling Guide version 9.5.3, ADINA R&D, Inc (2019). Harbor Drive, P.O. Box C700, West Conshohocken, PA, 19428–2959, USA (2021)
10. Pranata, Y.A., Suryoatmono, B.: Timber Structure, PT Remaja Rosdakarya (in Indonesian) (2019)
11. Persson, K.: Micromechanical Modelling of Wood and Fibre Properties, Doctoral Thesis, Unpublished, Department of Mechanics and Materials, Lund University, Sweden (2010)
12. Chen, W.F., Han, D.J.: Plasticity for Structural Engineers. J. Ross Publishing, pp. 99–100 (2007)
13. Karlinasari, L., Surjokusumo, S., Nugroho, N., Hadi, Y.S., Suryoatmono, B.: Bending strength prediction of wood beam, constructed from small specimens. In: 15th International Symposium Nondestructive of Wood, Duluth, Minnesota, USA, 10–12 September 2007 (2007)
14. Munoz, W., Mohammad, M., Salenikovich, A., Quenneville, P.: Determination of yield point and ductility of timber assemblies: In Search for a Harmonized Approach, Engineered Wood Products Association (2010)
15. Pranata, Y.A., Suryoatmono, B., Tjondro, J.A.: Numerical and experimental research of flexural strength of Indonesian timber. In: 1st National Seminar BMPTTSSI, University of North Sumatera, Indonesia (In Indonesian) (2011)

ORIGINALITY REPORT

20%

SIMILARITY INDEX

14%

INTERNET SOURCES

14%

PUBLICATIONS

4%

STUDENT PAPERS

PRIMARY SOURCES

1	journal.itb.ac.id Internet Source	4%
2	Yosafat Aji Pranata, Novi, Deni Setiawan, Vivi Arisandhy, Hendry Wong, Sofhie Angela Hagiyanto. "Chapter 25 Shear Strength of Red Meranti (<i>Shorea Spp.</i>) Timber at an Angle to the Grain", Springer Science and Business Media LLC, 2025 Publication	2%
3	ndl.ethernet.edu.et Internet Source	2%
4	Awal Sirajuddin Syahrani, Alimuddin Sam, Basri. "The effect of immersion with time and water variations on bending strength of malapoga wood (<i>Toona Ciliata M. Roem</i>)", MATEC Web of Conferences, 2020 Publication	2%
5	Y A Pranata, A Kristianto, A Darmawan. "Elastic Cross-Section Modulus Ratio of Jabon (<i>Anthocephalus cadamba</i> Miq.) Bolt-Laminated Timber Beams", IOP Conference Series: Materials Science and Engineering, 2021 Publication	1%
6	scholarworks.umass.edu Internet Source	1%
7	Ahmad M. Itani, Christophe Lanaud, Peter Dusicka. "Analytical evaluation of built-up	1%

shear links under large deformations",
Computers & Structures, 2003

Publication

8	mediatum.ub.tum.de Internet Source	1 %
9	lucris.lub.lu.se Internet Source	1 %
10	Moustafa M. Hussein, Khaled Nassar, Mohamed Darwish. "Mechanical Properties of Egyptian Casuarina Wood", Journal of Materials in Civil Engineering, 2019 Publication	1 %
11	Submitted to University of Sheffield Student Paper	1 %
12	viewmold.com Internet Source	1 %
13	worldwidescience.org Internet Source	1 %
14	www.slideshare.net Internet Source	1 %
15	Computational Structural Engineering, 2009. Publication	<1 %
16	www.guaduabamboo.com Internet Source	<1 %
17	Alaa Hassoon, Haider M. Al-Jelawy, Alaa Jaleel Naji, Dheyaa A. N. Alobaidi. "Chapter 7 Structural Behavior of Reinforced Concrete Spliced Beams Subjected to Repeated Loads: An Experimental Study", Springer Science and Business Media LLC, 2025 Publication	<1 %
18	mdpi-res.com Internet Source	<1 %

19 Lopez, A.. "Numerical model and experimental tests on single-layer latticed domes with semi-rigid joints", Computers and Structures, 200704 <1 %
Publication

20 Michal Kloiber, Jiří Kunecký, Miloš Drdácký, Jan Tippner, Václav Sebera. "Experimental and numerical analysis of semi-destructive device for in situ assessment of wood properties in compression parallel to grain", Wood Science and Technology, 2016 <1 %
Publication

21 ebin.pub <1 %
Internet Source

22 text.123docz.net <1 %
Internet Source

23 "The Advances in Civil Engineering Materials", Springer Science and Business Media LLC, 2019 <1 %
Publication

Exclude quotes Off

Exclude matches Off

Exclude bibliography On